

exhibiting a free swell index of between about 3.5 and about 5.0 and of a small diameter, having a density of between about 0.1 and about 0.8 g/cm³ and a thermal conductivity below about 1 W/m/°K.

5

12) The laminated sheet product of claim 11 wherein said coal exhibits a free swell index of between about 3.75 and about 4.5.

10

13) The laminated sheet product of claim 12 wherein said skins comprise a material selected from the group consisting of aluminum, steel, polymer sheet, inconel, titanium, refractory metals, fiber reinforced polymer sheet and paper.

15

14) The laminated sheet product of claim 12 wherein said sheet core has been carbonized.

15) The laminated sheet product of claim 12 wherein said sheet core is graphitized.

20

16) A semi-crystalline, largely isotropic, coal-based carbon foam having a thermal conductivity below about 1 W/m/°K.

17) The carbon foam of claim 1 having a density of between about 0.1 and about 0.8 g/cm³.

18) A coal-based carbon foam produced by the direct heating of comminuted coal particles in a pressure controlled mold and under a non-oxidizing atmosphere to a temperature ranging from about 300° C to about 700° C.

19) A method for producing carbon foam comprising directly heating comminuted coal particles in a pressure controlled mold to a temperature ranging from about 300° C to about 700° C.

20) A method for producing a coal-based carbon foam comprising:

A) comminuting coal containing adequate volatiles to permit foaming thereof upon the application of heat, to a small particle size to form a ground coal;

C) placing said ground coal into a mold;

D) heating said ground coal in said mold under a non-oxidizing atmosphere to a temperature and for a period adequate to produce a controlled foaming of said coal to form a preform; and

E) controllably cooling said preform.